

FORMATI / SIZES










| | 30x240 12"x96" | 30x120 12"x48" | 20x120 8"x48" | 7,5x60 3"x24" | 40x120 16"x48" |
|--------------------|----------------|----------------|---------------|---------------|----------------|
| | 297x2390 | 297x1195 | 197x1195 | | 397x1195 |
| | RT | RT | RT | N.RT | RT |
| | 9 mm | 9 mm | 9 mm | 8,5 mm | K2 20 mm |
| BEAT BROWN | | ● | ● ■ | ● | |
| BEAT IVORY | | ● | ● ■ | ● | |
| BEAT GREY | ● | ● | ● ■ | ● | ▲ |
| BEAT TAUPE | | ● | ● ■ | ● | |
| BEAT WALNUT | ● | ● | ● ■ | ● | ▲ |

● Natural R9 | ■ Grip R10 | ▲ Structured R11

MISURE, PESI ED IMBALLI / SIZE, WEIGHT AND PACKAGING

| FORMATO SIZE | SPESSORE THICKNESS | PZ/SCATOLA PIECES/BOX | MQ/SCATOLA SQM/BOX | KG/SCATOLA KG/BOX | MQ/PALLET SQM/PALLET | KG/PALLET KG/PALLET | SCATOLA/PALLET BOX/PALLET |
|------------------|-----------------------|--------------------------|-----------------------|----------------------|-------------------------|------------------------|------------------------------|
| 30x240 | 9 mm | 1 | 0,72 | ≅ 15,31 | 51,62 | ≅ 1187,32 | 72 |
| 30x120 | 9 mm | 4 | 1,44 | ≅ 30,50 | 23,04 | ≅ 501,00 | 16 |
| 20x120 | 9 mm | 6 | 1,44 | ≅ 28,25 | 51,84 | ≅ 1030,00 | 36 |
| 7,5x60 | 8,5 mm | 6 | 1,08 | ≅ 23,00 | 25,92 | ≅ 565,00 | 24 |
| 40x120 K2 | 20 mm | 2 | 0,96 | ≅ 41,80 | 23,04 | ≅ 1016,20 | 24 |

INFORMAZIONI TECNICHE / TECHNICAL FEATURES

| INFORMAZIONI TECNICHE TECHNICAL FEATURES | NORMA NORM EN 14411 - ISO 13006 | REQUISITI PRESCRITTI REQUIRED VALUES | VALORI VALUES |
|--|---------------------------------------|---|---|
|  DIMENSIONI RETTIFICATO SIZES RECTIFIED | UNI EN ISO 10545-2 | lunghezza-larghezza / lenght-width ±0,3% (±1,0 mm max) spessore / thickness ±0,0% (±0,5 mm max) ortogonalità / rectangularity ±0,3% (±1,5 mm max) rettilinearità / straightness ±0,3% (±0,8 mm max) planarità / flatness ±0,4% (±1,8 mm max) qualità superficie / surface quality ≥95% | CONFORME COMPLIANT |
|  ASSORBIMENTO ACQUA WATER ABSORPTION | UNI EN ISO 10545-3 | ≤0,5% | ≤0,1% |
|  RESISTENZA A ROTTURA BREAKING STRENGTH | UNI EN ISO 10545-4 | R≥35 N/mm ² S≥700 N (<7,5 mm) S≥1300 N (≥7,5 mm) | CONFORME COMPLIANT |
|  RESISTENZA ABRASIONE PROFONDA (UGL - Matt) DEEP ABRASION RESISTANCE (UGL - Matt) | UNI EN ISO 10545-6 | ≤175 mm ³ | ≤150 mm ³ |
|  RESISTENZA SHOCK TERMICI THERMAL SHOCK RESISTANCE | UNI EN ISO 10545-9 | resistenza / resistant | CONFORME COMPLIANT |
|  RESISTENZA AL GELO FROST RESISTANCE | UNI EN ISO 10545-12 | resistenza / resistant | CONFORME COMPLIANT |
|  RESISTENZA CHIMICA CHEMICAL RESISTANCE | UNI EN ISO 10545-13 | resistenza / resistant | CONFORME COMPLIANT |
|  RESISTENZA ALLE MACCHIE RESISTANCE TO STAINS | UNI EN ISO 10545-14 | pulibile / cleanable | CONFORME COMPLIANT |
| | DIN 51130 | R prodotto / product | R >0,40 >0,42 |
|  CLASSIFICAZIONE ALTISDRUCCIOLO ASSESSMENT OF SLIP RESISTANCE | B.C.R.A. (COF) | >0,40 bagnato / wet | 30x240 - 30x120 - 20x120 - 7,5x60 R9 CONFORME COMPLIANT |
| | | | 20x120 R10 CONFORME COMPLIANT |
| | ANSI A137.1 2012 (DCOF) | >0,42 bagnato / wet | 40x120 K2 R11 CONFORME COMPLIANT |

Piastrelle pressate a secco - Conforme alla norma EN 14411 e ISO 13006 appendice G gruppo B1-a con E ≤0,5%
Dry pressed tiles - Compliant with standards EN 14411 and ISO 13006 annex G group B1-a with E ≤0,5%